

LUBA-print 280/W

TECHNICAL INFORMATION

Chemical description:	Wax dispersion / Wachsdispersion
Application/properties:	Waterbased lacquers and coating systems: to improve slip behaviour and hydrophoby.
Processing information:	2 - 6 % of this wax dispersion to be added to the lacquer or coating while stirring
Solid:	Hydrocarbon combination
Emulsifier-system:	anionic
Solvent:	Water
Technical data:	Colour white

	Minimum	Maximum	Method
Active content	49,0 %	51,0 %	Sartorius MA 100 infrared drier
Drop point	45 °C	51 °C	DIN ISO 2176 (solid wax)
pH-Value	9,0	10,5	DIN ISO 976
Particle size d98 <=		5,0 µm	Single pass test
Density	0,93 g/ccm	0,95 g/ccm	Pyknometer DIN EN ISO 2811-1
Viscosity	20 mPa.s	80 mPa.s	Rheolab MC1 DIN 53019 1.291s-1

These data are also part of the test certificate and the specification.

Storage: In original closed containers lasting at least 12 months at temperatures between 5-35°C. Stir well before use!
Protect from frost! After long storage, particularly after usage of some of the product, evaporation of water is possible and visible signs of particles may be present. We therefore recommend filtration of the product before use.

欢迎使用以下方式与我们联系，以获取更多产品信息、样品支持和技术服务：



工厂：中国上海市青浦区崧泽大道 5350 号 电话：+86-21-32513560 传真：+86-21-32513556
免费咨询热线：400-021-8700 网址：www.titanos.cn 微信服务号：yt-service 微信订阅号：e-titanos