

AnTec C-OP

Ultrafine Calcined Kaolin

Product Description

AnTec C-OP is an engineered and structured calcined kaolin that has been dehydroxylated by precisely-controlled heat treatment for removal of crystalline-bound hydroxyl groups to maximally keep reactivity. AnTec C-OP is highly pulverized for better dispersion and provides excellent opacity.

Application information

Due to its high reactivity AnTec C-OP features excellent opacity, medium oil absorption and excellent dispersion. It is highly recommended for use in high grade products.

In coatings application, it works well as an extender to maximally replace TiO₂ and provides excellent opacity and color extension while maintaining film integrity.

In E-coatings it demonstrates satisfactory effects due to its low salt content and high salt spray resistance properties.

Typical Properties								
Appearance				White Powder				
Physical Form				Highly Pulverized Powder				
ISO Brightness (%)				91±1				
Screen Residue, 325 Mesh (%)				<0.003				
Free Moisture @ 105 deg C (%) as produced				<0.5	<0.5			
pH (28% solids)				5.0-	5.0-7.0			
Specific Gravity (g/cm³)				2.53	2.53			
Sedigraph Particle Size (%<2μm)				84±2				
Oil Absorption (g/100g)				70-7	70-75			
Bulk Density (kg/m³)				350				
Hegman				>4.0				
Chemical Components (%)								
SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	K₂O	Na₂O	CaO	MgO	
52.0±1	45.0±1	≤0.50	≤0.80	≤0.10	≤0.20	≤0.50	≤0.20	

Anpeak Specialty Minerals Co., Ltd owns ISO 9001:2015, ISO 14001:2015 and ISO 45001:2018 certificates.

The above typical properties are for general information only and should not be used for specification purposes. Performance characteristics may vary depending on specific application. All products should be tested in customer's formulation prior to use.

Anpeak Specialty Minerals Co., Ltd.

Beiping Circular Economy Park, PingLu District, Shuozhou City, Shanxi Province, PR China 036800 Tel +86 349 6076206 Fax: +86 349 6076204 Email: victor.he@anpeak.com.cn helen.mao@anpeak.com.cn http://www.anpeak.com.cn